

**210-65 AQUA BORNE INTERIOR/EXTERIOR PRIMER**  
**ACCENT BASE**

Graham's Accent Base Primer is specially designed for application as a deep color primer for use under dark colors. It has good adhesion to clean glossy surfaces and to galvanized metal.

**USES:** Accent Base Primer is ideal for porous surfaces such as **INTERIOR**/plaster, drywall, wood, concrete block, cement and **EXTERIOR**/trim, siding T111 board, rough sawn lumber, cement, stucco, asbestos and brick. Also for galvanized metal such as ductwork, gutters, downspouts.

**MATERIAL PREPARATION:** Ready to use from can; thin sparingly with water if necessary; mix well before use.

**SURFACE PREPARATION:** Surface must be clean, free from dust, dirt, grease, oil, soot, chalk, mildew, etc. **INTERIOR** - Fill nail holes and tape joints with patching plaster or joint cement. Sand smooth and spot prime with this product. **EXTERIOR** - Caulk joints and fill holes where necessary. All old, loose flaking or peeling paint must be removed. Spot prime all bare wood with this product.

**APPLICATION:** Use universal colorants only for tinting. Do not use when room or wall temperature is less than 50°F. Apply by brush, roller or spray. Apply full even coats and always work to a wet edge.

**AIRLESS SPRAY:** Use airless spray equipment capable of maintaining 80-100 lbs. Input pressure with a 28:1 to 30:1 airless pump. Use 17 thru 31 tips. Output rate will vary with tip size and number of guns in operation.

**PRODUCT SPECIFICATIONS**

<b><u>COLOR:</u></b>	Deep Color Primer
<b><u>60° GLOSS:</u></b>	6 max
<b><u>85° SHEEN:</u></b>	15 max (low)
<b><u>VEHICLE:</u></b>	Acrylic resin emulsion, exterior type
<b><u>PIGMENTATION:</u></b>	Titanium dioxide (type III) and aluminum silicate. Factory colors use light fast pigments free of heavy metals and toxic materials.
<b><u>SOLVENT:</u></b>	Water and non-toxic glycols. VOC 129g/L; 1.08 lbs./gal
<b><u>FLAMMABILITY:</u></b>	N/A
<b><u>% VEHICLE SOLIDS (WEIGHT):</u></b>	20.5
<b><u>% PIGMENT (WEIGHT):</u></b>	26
<b><u>% SOLVENT (WEIGHT):</u></b>	53.5
<b><u>% TOTAL SOLIDS (WEIGHT):</u></b>	46.5
<b><u>% TOTAL SOLIDS (VOLUME):</u></b>	34
<b><u>VISCOSITY:</u></b>	95-110 KU
<b><u>THEORETICAL COVERAGE:</u></b>	300 sq.ft/gal=5.3 wet mils=1.8 dry mils 400 sq.ft/gal=4.0 wet mils=1.4 dry mils 500 sq.ft/gal=3.2 wet mils=1.1 dry mils
<b><u>RECOMMENDED COVERAGE:</u></b>	400 square feet per gallon
<b><u>WEIGHT PER GALLON:</u></b>	10.2 lbs.
<b><u>DRY, SET TO TOUCH:</u></b>	1 hour
<b><u>DRY HARD:</u></b>	2 hours (recoat)
<b><u>CLEAN UP SOLVENT:</u></b>	Warm, soapy water
<b><u>TYPE OF CURE:</u></b>	Coalescence
<b><u>TINTING:</u></b>	Universal colorants only