

## **247-75 DURA KING LATEX GLOSS BARN PAINT**

This quality Latex Barn Paint can be used for practically all types of new or previously coated exterior surfaces. It is fume and mildew resistant, alkali resistant, blister resistant and fade resistant. It is self-priming on painted surfaces on good condition. Applies easily and quickly. May be recoated in one to two hours. You'll be amazed at how easy it goes on. Needs only stirring and you are ready to paint. No thinners or special additives of any kind are needed.

**USES:** Previously painted wood, hardboard and masonry surfaces in good condition.

**MATERIAL PREPARATION:** Mix well before using. Thinning not recommended. If necessary, use clean water sparingly.

**SURFACE PREPARATION:** Previously painted surfaces should be washed with strong detergent (trisodium phosphate) and water to remove chalk, dirt, grease, oil or wax. Prime new or unsealed wood and hardboard with quality exterior primer. Caulk open construction joints, countersink nails, prime and fill with putty.

**APPLICATION:** Do not use when temperature is less than 50°F. Avoid painting in hot, direct sun. Apply by brush, roller or spray. Apply full, even coats and always work to a wet edge.

**AIRLESS SPRAY:** Use airless spray equipment capable of maintaining 80-100 lbs. Input pressure at 28:1 to 30:1 airless pump. Use .017 to .026 inch tips.

247-75

**PRODUCT SPECIFICATIONS**

<b><u>COLOR:</u></b>	Red
<b><u>60° GLOSS:</u></b>	40-60
<b><u>85° SHEEN:</u></b>	45-65 range
<b><u>VEHICLE:</u></b>	Vinyl copolymer resin and soya alkyd resin
<b><u>PIGMENTATION:</u></b>	Red oxide
<b><u>SOLVENT:</u></b>	Water and EPA exempt glycols. VOC 134g/L; 1.12 lbs/gal.
<b><u>FLAMMABILITY:</u></b>	N/A
<b><u>% VEHICLE SOLIDS (WEIGHT):</u></b>	26
<b><u>% PIGMENT (WEIGHT):</u></b>	11
<b><u>% SOLVENT (WEIGHT):</u></b>	63
<b><u>% TOTAL SOLIDS (WEIGHT):</u></b>	37
<b><u>% TOTAL SOLIDS (VOLUME):</u></b>	28
<b><u>VISCOSITY:</u></b>	90-95KU
<b><u>RECOMMENDED COVERAGE:</u></b>	400 square feet per gallon
<b><u>WEIGHT PER GALLON:</u></b>	9.5
<b><u>DRY, SET TO TOUCH:</u></b>	30 minutes
<b><u>DRY HARD:</u></b>	24 hours
<b><u>CLEAN UP SOLVENT:</u></b>	Warm, soapy water
<b><u>TYPE OF CURE:</u></b>	Latex coalescence and oxidation
<b><u>TINTING:</u></b>	None