

## **462-SERIES ELITE INTERIOR LATEX SEMI-GLOSS ENAMEL**

Elite Acrylic Semi-Gloss Enamel combines the easy application methods of latex with a semi-gloss finish that rivals the washability and long life of the best oil base enamels. Made with an acrylic resin, this product forms a paint film which will retain its elasticity, color and fresh look for years. It is self-leveling with excellent flow that created a smooth china-like appearance impervious to most stains with virtually no odor. It has good one-coat hiding and will not haze over as do many alkyd-based paints.

**USES:** As a finish coat on woodwork, doors, trim and as a wall finish in kitchen and playroom areas. Also as a finish coat for masonry and properly primed metal.

**MATERIAL PREPARATION:** Ready to use from can; thin sparingly with water if necessary. Mix well before using.

**SURFACE PREPARATION:** All previously painted surfaces should be cleaned of all dirt, grease, oil or wax. Glossy surfaces should be scuff-sanded. Unpainted wood should be primed with enamel undercoater. The use of a block filler on cement or cinder blocks is recommended for best appearance.

**APPLICATION:** Do not use when room or wall temperature is less than 50°F. Apply by brush, roller or spray. Apply full even coats and always work to a wet edge. Two coats are recommended on new work where paint is badly needed.

**AIRLESS SPRAY:** Use airless spray equipment capable of maintaining 80-100 lbs. Input pressure with a 28:1 or 30:1 airless pump. Use 17 to 21 thou tips. Output will vary with tip size and number of guns in operation.

462-series

## **PRODUCT SPECIFICATIONS**

<b><u>COLOR:</u></b>	White Tintable, stock colors and bases
<b><u>60° GLOSS:</u></b>	40-55
<b><u>85° SHEEN:</u></b>	60-85
<b><u>VEHICLE:</u></b>	Acrylic based resin emulsion
<b><u>PIGMENTATION:</u></b>	Titanium dioxide and EPA approved silicates. All pigments are free of heavy metals and toxic materials.
<b><u>SOLVENT:</u></b>	Water and glycols. Contains no ammonia or volatile amines. VOC 155g/L; 1.29 lbs/gal.
<b><u>FLAMMABILITY:</u></b>	Not applicable
<b><u>% VEHICLE SOLIDS (WEIGHT):</u></b>	24 (462-49)
<b><u>% PIGMENT (WEIGHT):</u></b>	24
<b><u>% SOLVENT (WEIGHT):</u></b>	52
<b><u>% TOTAL SOLIDS (WEIGHT):</u></b>	48
<b><u>% TOTAL SOLIDS (VOLUME):</u></b>	34.5
<b><u>VISCOSITY:</u></b>	95-100
<b><u>REDUCED VISCOSITY:</u></b>	85-90 KU reduced 5% with water. Further reduction not recommended.
<b><u>THEORETICAL COVERAGE:</u></b>	300 sq.ft/gal=5.3 wet mils=1.9 dry mils 400 sq.ft/gal=4.0 wet mils=1.4 dry mils 500 sq.ft/gal=3.2 wet mils=1.2 dry mils
<b><u>RECOMMENDED COVERAGE:</u></b>	400 square feet per gallon
<b><u>WEIGHT PER GALLON:</u></b>	10.6 lbs.
<b><u>DRY, SET TO TOUCH:</u></b>	30 minutes
<b><u>DRY HARD:</u></b>	2-3 hours; recoat 3 hours
<b><u>CLEAN UP SOLVENT:</u></b>	Warm, soapy water
<b><u>TINTING:</u></b>	Universal colorants only