

602-SERIES ELITE ACRYLIC LATEX FLAT WALL PAINT

The 602-series Elite Latex Flat Wall Paint is a premium latex and a spatter resistant ceiling white that is easily applied and dries quickly with virtually no odor to uniform dead flat finishes. The high solids content of this line hides surface defects and permits single coat coverage in many instances. Excellent adhesion, hold-out, sealing properties and alkali resistance combine to give the finished coats long life and easy maintenance. Excellent touch-up.

USES: Interior only. All walls and ceilings made of plaster, drywall, composition board, concrete and masonry block. Can be used over secure wallpaper.

MATERIAL PREPARATION: Use as supplied. If necessary, thin sparingly with clean water.

SURFACE PREPARATION: Wash previously painted surfaces with a strong detergent to remove all dirt, grease, oil and wax. Scuff sand glossy surfaces. Repair all cracks and nail holes with patching plaster, sand smooth and spot prime with this paint. All new surfaces should be clean, smooth and primed prior to painting. Use any quality wall primer over drywall. Alkyd base primer sealer is recommended over new plaster after curing 30 days. Prime unpainted wood with enamel undercoater. Use metal primer over metal.

APPLICATION: Use universal colorants only for tinting. Do not use when room or wall temperature is below 50°F. Apply by brush, roller or spray. Apply full even coats and always work to a wet edge. Avoid excessive brushing or rolling.

AIRLESS SPRAY: Use airless spray equipment capable of maintaining 80-100 lbs. Input pressure with a 28:1 to 30:1 airless pump. Use 19 to 26 thou tips. Output rate will vary with tip size and number of guns in operation.

602-series

PRODUCT SPECIFICATIONS

<u>COLOR:</u>	White Tintable, Colors and Bases
<u>60° GLOSS:</u>	4 max (dead Flat)
<u>85° SHEEN:</u>	10 max
<u>VEHICLE:</u>	Vinyl acrylic resin emulsion in water
<u>PIGMENTATION:</u>	Titanium dioxide, calcium carbonate and EPA approved silicates. All pigments are free of heavy metals and toxic materials.
<u>SOLVENT:</u>	Water and glycols. Contains no ammonia or volatile amines. VOC 119g/L; 0.99 lbs/gal.
<u>FLAMMABILITY:</u>	Not applicable
<u>% VEHICLE SOLIDS (WEIGHT):</u>	11 (602-49)
<u>% PIGMENT (WEIGHT):</u>	43
<u>% SOLVENT (WEIGHT):</u>	46
<u>% TOTAL SOLIDS (WEIGHT):</u>	54
<u>% TOTAL SOLIDS (VOLUME):</u>	34.5
<u>VISCOSITY:</u>	100-105 KU
<u>THEORETICAL COVERAGE:</u>	300 sq.ft/gal=5.3 wet mils=1.9 dry mils 400 sq.ft/gal=4.0 wet mils=1.4 dry mils 500 sq.ft/gal=3.2 wet mils=1.2 dry mils
<u>RECOMMENDED COVERAGE:</u>	400 square feet per gallon
<u>WEIGHT PER GALLON:</u>	11.8 lbs.
<u>DRY, SET TO TOUCH:</u>	One hour
<u>DRY HARD:</u>	Three hours (recoat)
<u>CLEAN UP SOLVENT:</u>	Warm, soapy water
<u>TYPE OF CURE:</u>	Coalescence
<u>TINTING:</u>	Universal colorants