

613-49 ELITE ALKYD FLAT WALL PAINT

This wall paint is a tough, high-hiding alkyd based interior flat enamel. The high pigment solids and low side sheen of this finish fills and hides surface imperfections on areas being painted. A special alkyd resin and solvent blend give this flat excellent brush and roller application. This product is a recommended choice for use in high traffic areas.

USES: Interior surfaces only. Plaster, drywall, walls and ceilings. Interior woodwork.

MATERIAL PREPARATION: Mix well before using.

SURFACE PREPARATION: All surfaces should be cleaned of chalk, dust, dirt, greased, oil or wax. Sand new wood surfaces and prime with enamel undercoater. New plaster must be hard and dry before finishing. Prime new plaster with alkyd primer sealer. Cracking or peeling paint on old surfaces should be removed, sanded, filled and primed. Glossy surfaces should be scuff sanded.

APPLICATION: Do not use when room or wall temperature is less than 45°F. Apply by brush, roller or spray. Apply full even coats and always work to a wet edge.

AIRLESS SPRAY: Use airless spray equipment capable of maintaining 80-100 lbs. Input pressure at a 28:1 to 30:1 airless pump. Use .017 to .026 tips.

PRODUCT SPECIFICATIONS

<u>COLOR:</u>	613-49 White Tintable only
<u>60° GLOSS:</u>	3 max (dead flat)
<u>85° SHEEN:</u>	8 max (low)
<u>VEHICLE:</u>	Alkyd resin
<u>PIGMENTATION:</u>	Titanium dioxide (type III), silicates and non-crystalline silica
<u>SOLVENT:</u>	Low odor mineral spirits. VOC meets regulation of 250g/L; 2.10 lbs/gal
<u>FLAMMABILITY:</u>	105°F (combustible)
<u>% VEHICLE SOLIDS (WEIGHT):</u>	26.3
<u>% PIGMENT (WEIGHT):</u>	51
<u>% SOLVENT (WEIGHT):</u>	22.7
<u>% TOTAL SOLIDS (WEIGHT):</u>	77.3
<u>% TOTAL SOLIDS (VOLUME):</u>	70.3
<u>VISCOSITY:</u>	100-110 KU
<u>THEORETICAL COVERAGE:</u>	300 sq.ft/gal=5.3 wet mils=3.7 dry mils 400 sq.ft/gal=4.0 wet mils=2.8 dry mils 450 sq.ft/gal=3.6 wet mils=2.5 dry mils
<u>RECOMMENDED COVERAGE:</u>	400 square feet per gallon
<u>WEIGHT PER GALLON:</u>	8.6 lbs.
<u>DRY, SET TO TOUCH:</u>	One hour
<u>DRY HARD:</u>	12 hours (recoat)
<u>CLEAN UP SOLVENT:</u>	Mineral spirits or paint thinner
<u>TINTING:</u>	Universal colorants