

## **752-SERIES ELITE CHILDPROOF ACRYLIC LATEX SATIN ENAMEL**

The 752-series of Elite Childproof Satin Enamels are interior water based acrylic coatings which dry quickly to low gloss, low sheen finishes. These enamels are noted for their excellent brushing and rolling properties, with virtually no odor and good flow and leveling. The tough resin in the satin enamels gives them outstanding durability, washability and scrub resistance. They are recommended for use in high traffic areas.

**USES:** As a finish coat on woodwork, doors, trim and as a wall finish in kitchen and playroom areas. Also as a finish coat on masonry and properly primed metal.

**MATERIAL PREPARATION:** Ready to use from can; thin sparingly with water if necessary. Mix well before using.

**SURFACE PREPARATION:** All previously painted surfaces should be cleaned of all dirt, grease, oil or wax. Glossy surfaces should be scuff sanded. Unpainted wood should be primed with metal primer. No special primer is needed on masonry; however, the use of a block-filler on cement or cinder blocks is recommended for best appearance.

**APPLICATION:** Use universal colorants for tinting. Do not use when room or wall temperature is less than 50°F. Apply by brush, roller or spray. Apply full even coats and always work to a wet edge. Two coats are recommended on new work or on old work where paint is needed.

**AIRLESS SPRAY:** Use airless spray equipment capable of maintaining 80-1200 lbs. Input pressure with a 28:1 or 30:1 airless pump. Use 17 to 21 thou tips. Output rate will vary with tip size and number of guns in operation.

752-series

## **PRODUCT SPECIFICATIONS**

<b><u>COLOR:</u></b>	White Tintable, Decorator White and Bases
<b><u>60° GLOSS:</u></b>	20-30
<b><u>85° SHEEN:</u></b>	Low
<b><u>VEHICLE:</u></b>	Acrylic based resin emulsion
<b><u>PIGMENTATION:</u></b>	Titanium dioxide (type III) and aluminum silicate. All pigments are free of heavy metals and toxic materials.
<b><u>SOLVENT:</u></b>	Water, ethylene glycol and glycol ether. Contains no ammonia or volatile amines. VOC 121g/L; 1.00 lb/gal. (White Tintable)
<b><u>FLAMMABILITY:</u></b>	Not applicable
<b><u>% VEHICLE SOLIDS (WEIGHT):</u></b>	21 (752-49)
<b><u>% PIGMENT (WEIGHT):</u></b>	29
<b><u>% SOLVENT (WEIGHT):</u></b>	50
<b><u>% TOTAL SOLIDS (WEIGHT):</u></b>	50
<b><u>% TOTAL SOLIDS (VOLUME):</u></b>	36
<b><u>VISCOSITY:</u></b>	95-100 KU
<b><u>THEORETICAL COVERAGE:</u></b>	533 sq.ft/gal=3 wet mils=1.1 dry mils 400 sq.ft/gal=4 wet mils=1.5 dry mils 320 sq.ft/gal=5 wet mils=1.8 dry mils
<b><u>RECOMMENDED COVERAGE:</u></b>	400 square feet per gallon
<b><u>WEIGHT PER GALLON:</u></b>	10.9 - 11.1 lbs.
<b><u>DRY, SET TO TOUCH:</u></b>	30 minutes
<b><u>DRY HARD:</u></b>	3 hours (recoat)
<b><u>CLEAN UP SOLVENT:</u></b>	Warm, soapy water
<b><u>TINTING:</u></b>	Universal colorants only