

800-74 CLEAR SANDING SEALER AND FINISH

800-74 Clear Sanding Sealer and Finish is a fast drying clear semi-gloss coating specially designed for professional, high volume finishing operations. Recommended for coating wood cabinets, furniture and interior doors, sash and trim. Excellent for use as a first (sealer) coat for subsequent coats of varnish. Also suitable as a finish coat in some applications.

USES: Interior use on wood floors, stairs, paneling, trim, cabinets, furniture.

MATERIAL PREPARATION: Material ready for use as supplied. Mix well before use.

SURFACE PREPARATION: All wood surfaces must be dry and cleaned of all dirt, dust, oil and wax. Sand new work, apply stain and dry. Fill countersunk nail holes and other imperfections with tinted filler and apply this product. Scuff sand with fine paper or steel wool, wipe clean and apply finish coat of varnish or this finish if desired. Very hard urethane finish coats are not recommended over this sealer.

APPLICATION: Do not use when temperature is less than 30°F or higher than 90°F. Apply by quality bristle brush, mohair roller or spray. Apply full even coats, work with the grain and keep a wet edge. Use with adequate ventilation.

80074

PRODUCT SPECIFICATIONS

<u>COLOR:</u>	Clear
<u>60° GLOSS:</u>	45-60
<u>85° SHEEN:</u>	50-70 range
<u>VEHICLE:</u>	Vinyl Tolulene and polyhydric alcohol esters of linoleic-oleic, linoleic-palmitic and stearic acids, copolymer
<u>PIGMENTATION:</u>	Zinc stearate.
<u>SOLVENT:</u>	VMP Naphtha and Rule 66 low odor mineral spirits. VOC meets regulation of 550g/L; 4.60 lbs/gal.
<u>FLAMMABILITY:</u>	50-55°F Flammable
<u>% VEHICLE SOLIDS (WEIGHT):</u>	34.5
<u>% PIGMENT (WEIGHT):</u>	4.3
<u>% SOLVENT (WEIGHT):</u>	60.3
<u>% TOTAL SOLIDS (WEIGHT):</u>	39.7
<u>% TOTAL SOLIDS (VOLUME):</u>	33.0
<u>VISCOSITY:</u>	D-F (Gardner-Holdt) 100-150 cps.
<u>THEORETICAL COVERAGE:</u>	500 sq.ft/gal=3.2 wet mils=1.1 dry mils 600 sq.ft/gal=2.7 wet mils=0.9 dry mils
<u>RECOMMENDED COVERAGE:</u>	500-600 square feet per gallon (1.0 dry mils)
<u>WEIGHT PER GALLON:</u>	7.0 lbs.
<u>DRY, SET TO TOUCH:</u>	30 minutes
<u>DRY HARD:</u>	Three hours
<u>CLEAN UP SOLVENT:</u>	Paint thinner or mineral spirits
<u>TYPE OF CURE:</u>	Oxidation
<u>TINTING:</u>	Not recommended