

882-00 PRO FINISH LATEX BLOCK FILLER (AIRLESS SPRAY)

This Latex Block Filler is an interior/exterior product designed to change the porous appearance of concrete blocks or rough cast concrete to that of a smooth, even surface. It contains special aggregate fillers which fill and seal voids with minimum shrinking. These fillers will not clog tips in an airless spray operation. It provides an attractive, durable surface that requires no further finishing on interior surfaces. Exterior surfaces, however, must be re-coated with an exterior paint.

USES: Interior and exterior masonry surfaces - concrete or cinder blocks; rough cast concrete.

MATERIAL PREPARATION: Thinning not recommended. If necessary, use water sparingly.

SURFACE PREPARATION: All surfaces must be cleaned of dirt, excessive dust, grease, oil, wax or other foreign material that impair bonding of the filler. 882-00 can be applied over damp (not wet) surfaces.

APPLICATION: Do not use when temperature is less than 50°F. Apply by airless spray, roller or brush. Airless spray and back roll gives best full properties. Two coats may be desired for optimum fill over very porous material.

AIRLESS SPRAY: Use airless spray equipment capable of maintaining 80-100 lbs. input pressure with a 28:1 or 30:1 airless pump. Use .026 to .036 inch tips.

882-00

PRODUCT SPECIFICATIONS

<u>COLOR:</u>	White
<u>60° GLOSS:</u>	6 max
<u>85° SHEEN:</u>	15 max
<u>VEHICLE:</u>	Vinyl acetate/acrylic copolymer resin emulsion
<u>PIGMENTATION:</u>	Titanium dioxide, calcium carbonate, EPA approved silicates. All pigments are free of heavy metals and toxic materials.
<u>SOLVENT:</u>	Water and glycols (6%). VOC 072g/L; 0.60 lbs/gal.
<u>FLAMMABILITY:</u>	Not applicable
<u>% VEHICLE SOLIDS (WEIGHT):</u>	11
<u>% PIGMENT (WEIGHT):</u>	62
<u>% SOLVENT (WEIGHT):</u>	27
<u>% TOTAL SOLIDS (WEIGHT):</u>	70
<u>% TOTAL SOLIDS (VOLUME):</u>	51
<u>VISCOSITY:</u>	105-110 KU
<u>RECOMMENDED COVERAGE:</u>	75 to 100 square feet per gallon will vary with surface
<u>WEIGHT PER GALLON:</u>	13.6 - 13.9 lbs.
<u>DRY, SET TO TOUCH:</u>	One hour (16 mils)
<u>DRY HARD:</u>	3-6 hours (recoat 6 hours)
<u>CLEAN UP SOLVENT:</u>	Water
<u>TYPE OF CURE:</u>	Coalescence
<u>TINTING:</u>	Universal colorants only. 4oz. per gal. max